



UNIT B3  
SOUTH GYLE CRESCENT LANE  
EDINBURGH EH12 9EG

TEL: +44 (0)131 334 4999  
FAX: +44 (0)131 334 3987  
EMAIL: [enquiries@valtti.co.uk](mailto:enquiries@valtti.co.uk)  
[www.valtti.co.uk](http://www.valtti.co.uk)

## KIVA FLOOR LACQUER

### DESCRIPTION

Waterborne low-odour polyurethane-acrylate lacquer for use on interior wooden surfaces. Parquet-Ace Floor Lacquer is available in a gloss and semi-gloss finish.

### EXAMPLES OF USE

Parquet flooring, particle and floor boarding, etc. Parquet-Ace Floor Lacquer can be used on new or previously varnished interior surfaces. Parquet-Ace Floor Lacquer is not recommended for diamond pine, smoked oak or stabilized brown beech surfaces.

### TECHNICAL DATA

Solids Volume: approx. 32%  
Density: 1.0 kg/l  
Scrub Resistance: Good (DIN 53778)  
Chemical Resistance: Good (ISO 2812-1). Does not resist thinner.

EU VOC 2004/42/EC-limit value

(cat A/i) 140g/l(2010) Parquet-Ace Finishing Lacquer contains VOC max. 140g/l.

### SPECIFICATIONS

#### Preparation

Surfaces must be clean, dry, and free from grease, dirt, oil, wax, rust, all loose material and surface contamination. Completely remove existing lacquer or varnish coatings that are in poor condition. Fill cracks, nail holes, etc. with a good quality wood filler or by using a filler made by mixing Parquet-Ace Floor Priming Lacquer or Parquet-Ace Floor Lacquer with the wooden sanding dust. Ensure that all filled and glossy surfaces are thoroughly flattened down. Remove all sanding dust.

#### Priming

Prime new bare wood overall and if necessary spot prime all bare areas on previously lacquered or varnished wood with Parquet-Ace Floor Priming Lacquer as in accordance with priming lacquer data sheet.

### APPLICATION

Methods: brush, mohair roller or spreader. Polyester or nylon paint brushes are best suited for the application of the Floor Lacquer.  
Thinning: if necessary by up to 5% with water.

#### Painting Conditions

All surfaces to be painted must be dry, the temperature of the air at least 15°C, and the relative humidity of the air below 80%.

#### Painting

Stir lightly before use. Do not whip air into the lacquer. Apply two or three coats of Parquet-Ace Floor Lacquer working in the direction of the wood grain, allowing 1-3 hours between coats. Plan application route prior to applying Parquet-Ace Floor Lacquer.



UNIT B3  
SOUTH GYLE CRESCENT LANE  
EDINBURGH EH12 9EG

TEL: +44 (0)131 334 4999  
FAX: +44 (0)131 334 3987  
EMAIL: [enquiries@valtti.co.uk](mailto:enquiries@valtti.co.uk)

[www.valtti.co.uk](http://www.valtti.co.uk)

**Coverage**

10-15 m<sup>2</sup>/litre per coat. Spreading rates will depend upon many factors including texture, porosity, moisture content of the substrate and method of application.

**Drying Times**

At 23°C and 50% relative humidity of the air: normally touch-dry in one hour and recoatable after 3 hours. Avoid hard stress (abrasion, etc.) to the surface during the first two weeks after application. Do not lay coverings or carpets onto the surface during the first week after application as through-drying may be impaired.

**Cleaning of Tools**

Clean with water immediately after use.

**PREVENT ENVIRONMENTAL DAMAGE**

Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations.

**HEALTH AND SAFETY CLASSIFICATION**

according to EC Directive 99/45/EC

Not classified as hazardous for health. Handle with care, avoid prolonged contact with skin and breathing of spray mist.

A Material Safety Data Sheet is available on request.

**TRANSPORT**

ADR/RID -  
Protect from frost.